



Nitomortar 30

Chemical and abrasion resistant epoxy repair compound

Uses

For permanent repairs to concrete structure and cementitious substrates where strength, impermeability to water and resistance to aggressive chemicals is essential. Ideally suited for maintaining engineering, chemical handling and processing plants.

Advantages

- **Chemical Resistance** :Unaffected by wide range of acids, alkalis and industrial chemicals
- **Easily applied** :Designed for easy application to a fair finish
- **Quality** : Pre-weighed quality controlled materials ensure consistency and reduce risk of site errors
- **Proven performance** :Successful use proves for a wide variety of aggressive applications

Description

Nitomortar 30 is a three part solvent free combination of epoxy resin, modified amine hardeners filled with specially graded chemically inert aggregates with high crushing strength.

It is applied by trowel as a durable chemical resistant repair mortar 3-6 mm thick depending upon the requirement. The system includes Nitoprime 25 a two part epoxy resin primer and Nitomortar 30 which are both supplied in preweighed units ready for onsite mixing and application. The finished area has a slightly granular texture of uniform self colour. However, as the natural grade takes its colour from the aggregates which is subjected to variation, colour matching is not practicable with this grade.

Technical Support

Fosroc offers a technical support package to specifiers, end users and contractors as well as onsite technical assistance all over the country.

Properties

Curing characteristics at 30°C

Nitomortar 30

Pot life	:	30 min.
----------	---	---------

Initial hardness	:	16 hrs
------------------	---	--------

Full cure	:	7 days
-----------	---	--------

Mechanical characteristics @ full cure

Compressive strength	:	45 N/mm ²
----------------------	---	----------------------

Flexural strength	:	12 N/mm ²
-------------------	---	----------------------

Tensile strength	:	4.5 N/mm ²
------------------	---	-----------------------

Bond strength to concrete	:	3.0 N/mm ²
---------------------------	---	-----------------------

Nitoprime 25

Pot life	:	30 min. @ 30°C
----------	---	----------------

Maximum overlay time	:	30 min. @ 30°C
----------------------	---	----------------

Chemical Resistance

Acids

Hydrochloric 10%	Excellent
Sulphuric 10%	Excellent
Phosphoric 30%	Excellent
Nitric 10%	Good
Lactic 10%	Excellent
Citric 10%	Excellent

Alkalis

Sodium Hydroxide 30%	Excellent
Ammonia 10%	Excellent

Organic Solvents

Butanol	Good
White Spirit	Excellent
Oil/Grease/Petrol	Excellent
Xylene	Good
Acetone	Not resistant
Skydrol	Good

Sat. Sugar	Excellent
------------	-----------

Aqueous solutions

Conc. Bleach	Excellent
Sat. Urea	Excellent

Nitomortar 30

Those materials marked 'Good' are suitable for areas of occasional spillage where good housekeeping is in force.

All the above properties have been determined by laboratory controlled tests and are typical of those expected in practice.

Estimating

Packaging and Coverage

	Pack size	Approx. Coverage rate
Nitoprime 25	1 & 4 Ltr	5.5 - 6.5 m ² /Ltr.
Nitomortar 30	8 Ltr	2.67m ² @ 3mm thickness/pack 1.33m ² @ 6mm thickness/pack

The coverage rates are given for guidance only as actual quantities used will vary on nature of substrate and conditions on site.

Storage

Nitoprime 25 and Nitomortar 30 have a shelf life of 12 months if stored in unopened containers below 35°C.

Additional information

Fosroc manufactures a wide range of products specially designed for the repair and refurbishment of damaged reinforced concrete. This includes hand placed and spray grade repair mortars, fluid microconcretes, chemical resistant epoxy mortars and a comprehensive package of protective coatings. In addition, a wide range of complementary products are available.



Fosroc Chemicals (India) Pvt. Ltd.

Head Office

"Sapthagiri Palace", No.38,
II & III Floor, 12th Cross,
CBI Road, Ganganagar North,
Bangalore 560 032

Important note :

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard terms and conditions of sale, copies of which may be obtained on request. Whilst Fosroc endeavours to ensure that any advice, recommendation specification or information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products whether or not in accordance with any advice, specification, recommendation or information given by it.

telephone

++91 80-23551500

fax

++91 80-23551510

e-mail

enquiryindia@fosroc.com

Regional Offices

Bangalore

"Sapthagiri Palace", No. 38
II & III Floor, 12th Cross,
CBI Road, Ganganagar North,
Bangalore 560 032.
Ph:080-23551500
Fax : 080-23551510

Mumbai

1401/1402, 14floor,
A-Wing'The Great Eastern Summit'
Sector-15, CBD, Belapur
Navi Mumbai 400 614
Ph: 022 -43406800-04

Delhi

D-166 Sector 10
Noida,
UP 201 301
Ph:0120-4270620
Fax: 033-2499-0280

Kolkata

304, Jodhpur Park
Kolkata 700 068
Ph:033-65343188