



# Method Statement

## Renderoc RG

### Section A : General Comments

#### High temperature working

It is suggested that, for temperatures above 35°C, the following guidelines are adopted as good working practice:

- (i) Store unmixed materials in a cool (preferably temperature controlled) environment, avoiding exposure to direct sunlight.
- (ii) Keep equipment cool, arranging shade protection if necessary. It is especially important to keep cool those surfaces of the equipment, which will come into direct contact with the material itself.
- (iii) Try to avoid application during the hottest times of the day, arrange temporary shading as necessary.
- (iv) Make sufficient material, plant and labor available to ensure that application is a continuous process.
- (v) Where mixing water is required in the application of a product, it is advised to maintain such water at a maximum of 20°C

#### Equipment

It is suggested that the following list of equipment is adopted as a minimum requirement

<i>Protective clothing</i>	:	Protective overalls
	:	Good quality gloves, goggles and face mask
<i>Preparation equipment</i>	:	Wire brush
	:	Proprietary blasting equipment, air blower etc
<i>Mixing equipment</i>	:	Measuring jug
	:	1 KW slows speed drill, 400 or 500 rpm
	:	+ Fosroc <b>MR4</b> mortar mixing paddle
	:	+ Suitably sized mixing vessel, for single bag mixing, or
	:	Proprietary forced-action mixer for multiple bag mixing
<i>Application equipment</i>	:	Hand application trowel
	:	Wooden float
	:	Steel or plastic finishing float
	:	Finishing sponge

#### Application - points of note

Fosroc operates a policy to encourage the use, where possible, of registered applicators, since the long term performance of the materials is dependent upon proper application.

Fosroc Chemicals (India)  
Private Limited

"Sapthagiri Palace", No.38,  
II & III Floor, 12<sup>th</sup> Cross,  
CBI Road, Ganganagar North  
BANGALORE – 560 024

[www.fosroc.com](http://www.fosroc.com)

Telephone:

++ 91 80 2355 1500

++ 91 80 425 21900

fax:

++ 91 80 2355 1510

email:

[enquiryindia@fosroc.com](mailto:enquiryindia@fosroc.com)

Registered Office: 41<sup>st</sup> KM, NH4, Nelamangala Taluk, Bangalore Rural Dist - 562111



## Section B : Application Method

### 1.0 Surface preparation

Attention to full and proper preparation of the substrate is essential for complete repair adhesion.

- 1.1 The surface of the substrate should be thoroughly cleaned to remove all traces of dust, oil, paint, curing compounds, grease, corrosion deposits, algae or any unsound material which might affect subsequent bond between Renderoc RG and the substrate.
- 1.2 Oil and grease deposits are best removed by steam cleaning, detergent scrubbing or the use of a proprietary degreaser. The effectiveness of decontamination should be assessed by a pull-off test.
- 1.3 The substrate should further be 'roughened' to remove excess laitance, to expose pinholes & blowholes and to provide a mechanical key for subsequent application of Renderoc RG. This is most effectively achieved by the use of proprietary blast media, such that the fine aggregate is exposed but not polished.
- 1.4 Immediately prior to application of Renderoc RG, the prepared substrate should be blown clean with oil-free compressed air.

### 2.0 Substrate priming

- 2.1 All prepared areas should be thoroughly soaked with clean, potable water immediately prior to the application of Renderoc RG, such that the substrate is "saturated surface dry".
- 2.2 Since Renderoc RG is a micro concrete, reinforcing steel exposed shall be cleaned and coated with Nitozinc primer and surface shall be coated with Notobond AR to improve the adhesion between the two surfaces.

### 3.0 Mixing

Care should be taken to ensure that Renderoc RG is thoroughly mixed. In all cases the powder should be added to the water and mixed strictly in accordance with appropriate procedure.

#### 3.1 Mixing -

- a) For mixing Renderoc RG it will be necessary to mix using
  - a proprietary forced action mixer, or
  - Slow speed drill (400/500 rpm) + Fosroc **MR4** mortar paddle attachment.
- b) For each bag of Renderoc RG to be mixed, measure out and place approximately 13.0 liters of cool, potable water into the mixer (water quantity may vary slightly according to ambient temperature and desired consistency of mix).
- c) Always add the powder to the water. With the mixer in operation add one full bag of Renderoc RG, and mix continuously for 5 minutes until fully homogenous mix is obtained.

## 4.0 Application

Do not proceed with the application when rainfall is imminent, unless in a sheltered or protected position.

- 4.1 Before applying make sure that any formwork provided is slurry tight, then apply/pour fully mixed Renderoc RG to the prepared substrate, by suitable method. It should be applied with the minimum of working, and be allowed to partly set before finally trowelling to a smooth finish. For repair sections generally thicker than 100 mm it may be necessary to mix the Renderoc RG with properly graded 5 mm to 12 mm silt free aggregate to minimize the temperature rise.
- 4.2 Thickness of application should be in accordance with that laid down in the '**Application criteria**' section of the current product data sheet. The specifications mentioned there in should be strictly adhered to.

## 5.0 Finishing

- 5.1 Renderoc RG is finished by striking off with a straight edge and closing with a steel or plastic float. Note that water can be drawn to the surface if 'overworking with the float occurs, and an unsightly finish may result.
- 5.2 Damp sponges or plastic floats may be used to achieve a desired surface texture, but care should again be taken not to overwork the surface.

## 6.0 Curing

- 6.1 Curing of Renderoc RG is required. However, under extreme drying conditions - high temperatures, drying winds - refer to Section A.

## 7.0 Cleaning

- 7.1 All equipment should be washed with clean water immediately after use. Cured material can only be removed by mechanical means.

## Section C : Approval and variations

This method statement is offered by Fosroc as a 'standard proposal' for the application of Renderoc RG. It remains the responsibility of the Customer to determine the correct method for any given application. Where alternative methods are to be used, these must be submitted to Fosroc for comment, in writing, prior to the commencement of any work.