

# Trafficguard UR150

## Hard wearing, skid resistant, flexible protection system for car park decks

### Uses

Trafficguard UR150 is a polyurethane traffic deck system designed to provide an added level of protection to, new and existing, trafficked areas such as:

- Car park decks
- Car park ramps
- Aircraft hangers
- Transport depots; e.g. bus, coach, taxis etc
- Service centres, garages
- Workshops

### Advantages

- Flexible and bridges dynamic cracks
- Suitable for all zones in a car park
- Seamless and watertight
- Rapid application, reliable and safe
- UV resistant

### Description

Trafficguard UR150 is a multi-layer flooring system comprising a primer, flexible topcoat and wear course. All components are applied in the liquid phase and react chemically to form a tough, flexible, waterproof protective surface.

Trafficguard UR150 is available in a range of standard colours. Contact your local Fosroc office for full details.

### Properties

Elongation (ASTM D412)	: ca. 175%
Tensile Strength (ASTM D412)	: 8 N/mm <sup>2</sup>
Tear Resistance (ASTM D624)	: 18 N/mm <sup>2</sup>
Shore A Hardness (ASTM D2240)	: ca. 80
Overcoating time at 35°C	: 16 hours

### Chemical Resistance

Trafficguard UR150 is resistant to a range of chemicals including:

- Petrol, Engine Oil, Jet fuel, Brake fluid, Mineral spirit
- Diesel, Medium concentration acids
- Detergents etc.

For full details contact your local Fosroc office.

### Instructions for use

#### Surface Preparation

New concrete surfaces should have reached 80% of their intended physical properties - generally only achieved after a minimum curing period of 28 days. Existing concrete surfaces must be prepared to provide a clean, sound substrate.

Surfaces should be clean and dry with open capillary, free from laitance, oil and grease, curing compounds or other surface contaminants which may prevent full and proper adhesion of the primer. All blowholes, and other surface undulations should be repaired using an appropriate Fosroc product.

# Trafficguard UR150

---

## Application

### Primer

Apply Trafficguard UR150 Primer to the prepared surface at an application rate in the range of 0.2 to 0.3 ltr/m<sup>2</sup>. Quantity will depend on surface texture and porosity.

Whilst Trafficguard UR150 Primer is still wet, blind with Anti Slip Grain No. 2 at an estimated rate of between 0.4 - 0.8 kg/m<sup>2</sup>, leave to dry for 16 hours @ 35°C. Prior to the removal of excess antislip grain ensure that the grains are firmly embedded in the primer.

### Top Coat

Apply Trafficguard UR150 Top Coat to the primed surface at an application rate in the range of 0.4 to 0.5 ltr/m<sup>2</sup> per coat. For best results the Trafficguard UR150 Top Coat should be applied with a short haired lambswool roller.

### Wear Course

Apply Trafficguard UR150 Wear Course to the Trafficguard UR150 Topcoat at an application rate of 0.1 - 0.2 ltr/m<sup>2</sup> (100-200 microns wft) per coat.

Prior to trafficking allow the following cure periods:

Foot traffic : 24 hrs @ 25°C or 18 hrs @ 35°C

Vehicle traffic : 5 days @ 25°C or 72 hrs @ 35°C

Traffic marking lines may be applied using Trafficguard Line Marking Paint (TLMP) after five days from time of application.

### Cleaning

Tools and equipment should be cleaned immediately after use with Fosroc Solvent 102\*

## Estimating

### Supply

Trafficguard UR150 Primer	: 9 litre packs
Topcoat	: 18 litre packs
Wear course	: 20 litre packs
Antislip Grains No.2	: 18 litre packs
Coverage	
Primer	: 0.2 - 0.3 ltr/m <sup>2</sup>
Antislip Grain 2	: 0.4 - 0.8 kg/m <sup>2</sup>
Top coat	: 0.4 - 0.5 ltr/m <sup>2</sup> /coat
Wear Course	: 0.1 - 0.2 ltr/m <sup>2</sup> /coat
TLMP (per coat - 2-3 coats recommended)	: 5 m <sup>2</sup> /ltr

Note : The above coverage rates are given for guidance only as actual quantities used will vary depending upon the nature of substrate and conditions on site. It is strongly advised that trials are conducted to establish coverage rates.

### Technical Support

Fosroc offers a comprehensive technical support service to specifiers, and users and contractors. It is also able to offer on-site technical assistance, an AutoCAD facility and dedicated specification assistance in locations all over the world.

### Storage

#### Shelf life

When stored in warehouse conditions at less than 25°C. Trafficguard UR150 will have a shelf life of 12 months.

### Limitations

# Trafficguard UR150

---

- Trafficguard UR150 should not be applied on to surfaces which are known to or likely to suffer from rising damp or have a relative humidity greater than 75% as measured in accordance with BS8203 Appendix A or by Hammond concrete/mortar moisture tester type COCO.
- In conditions of high relative humidity i.e. 85-90%, good ventilation conditions are essential. Substrate temperature should be atleast 3°C above dew point.
- Do not proceed with application if precipitation is imminent, or temperatures are expected to drop below 7°C within 24 hours of application.

## High temperature working

It is suggested that, for temperatures above 35°C, the following guidelines are adopted as good working practice:

- Store material in a cool (preferably temperature controlled) environment, avoiding exposure to direct sunlight.
- Keep equipment cool, arranging shade protection if necessary. It is especially important to keep cool those surfaces of the equipment which will come in direct contact with the material itself.
- Try to eliminate application during the hottest times of the day.
- Make sufficient material, plant and labour available to ensure that the application is a continuous process.

## Precautions

## Health and safety

Trafficguard UR150 Primer and Nitoflor Sol should not come in contact with skin or eyes, nor should they be swallowed. Avoid inhalation of vapours and ensure adequate ventilation.

Some people are sensitive to resins, hardeners and solvents. Wear suitable protective clothing, gloves and eye/face protection. Barrier cream can provide additional skin protection.

Should accidental skin contact occur, remove immediately with a resin removing cream followed by washing with soap and water - do not use solvent.

The use of goggles is recommended, in case of accidental eye contamination, rinse immediately with plenty of water and seek medical advice.

If swallowed seek medical attention immediately - do not induce vomiting.

## Fire

Fosroc Solvent 102, Trafficguard UR150 Primer and Trafficguard UR150 wear course are flammable. Do not use near a naked flame.

Flash points

Fosroc Solvent 102	: 33°C
Trafficguard UR150 Primer	: 59°C
Trafficguard UR150 Wear course	: 23°C

# Trafficguard UR150

---

## Additional Information

Fosroc manufactures a wide range of complementary products which include :

- waterproofing membranes & waterstops
- joint sealants & filler boards
- cementitious & epoxy grouts
- specialised flooring materials

Fosroc additionally offers a comprehensive package of products specifically designed for the repair and refurbishment of damaged concrete. Fosroc's 'Systematic Approach' to concrete repair features the following :

- hand-placed repair mortars
- spray grade repair mortars
- fluid micro-concretes
- chemically resistant epoxy mortars
- anti-carbonation/anti-chloride protective coatings
- chemical and abrasion resistant coatings

For further information on any of the above, please consult your local Fosroc office - as below.



## Fosroc Chemicals (India) Pvt. Ltd.

### Head Office

"Sapthagiri Palace", No.38,  
II & III Floor, 12th Cross,  
CBI Road, Ganganagar North,  
Bangalore 560 032

### Important note :

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard terms and conditions of sale, copies of which may be obtained on request. Whilst Fosroc endeavours to ensure that any advice, recommendation specification or information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products whether or not in accordance with any advice, specification, recommendation or information given by it.

### telephone

++91 80-23551500

### fax

++91 80-23551510

### e-mail

enquiryindia@fosroc.com

### Regional Offices

#### Bangalore

"Sapthagiri Palace", No. 38  
II & III Floor, 12th Cross,  
CBI Road, Ganganagar North,  
Bangalore 560 032.  
Ph:080-23551500  
Fax : 080-23551510

#### Mumbai

1401/1402, 14floor,  
A-Wing'The Great Eastern Summit'  
Sector-15, CBD, Belapur  
Navi Mumbai 400 614  
Ph: 022 -43406800-04

#### Delhi

D-166 Sector 10  
Noida,  
UP 201 301  
Ph:0120-4270620  
Fax: 033-2499-0280

#### Kolkata

304, Jodhpur Park  
Kolkata 700 068  
Ph:033-65343188

