



Proofex ORG

Loose laid reinforced TPO waterproofing membrane

Uses

Provides a continuously loose laid waterproof membrane system for building and civil engineering structures.

- Podiums, parking decks, flat roofs and garden roofs waterproofing.
- Basement waterproofing
- Lining of ponds, canals, reservoirs and landfills.

Advantages

- Environment friendly, no VOC, no plasticisers, non toxic.
- Cold applied.
- Reinforced grade to achieve aesthetically pleasing finish.
- High resistance to weathering and UV.
- Fast application
- Welded joints for maximum watertightness
- No separate layers required on to EPS.
- Excellent long term performance

Description

TPO/FPA (Flexible Polypropylene Alloy) reinforced membrane produced by extrusion of granules resulting from the incorporation of ethylene propylene rubber into a polypropylene matrix together with other additives as appropriate to the type of membrane

The membrane is manufactured in two different colours, it is coloured grey on top and black on the underside. This helps to identify any damages that may occur during application.

Specification

The membrane shall be a 1.5mm thick loose laid reinforced TPO/FPA membrane with hot air welded seams.

Typical Properties

Thickness(l) (EN 1849-2)	: 1.5 mm
Standard Colours(2)	: Black - Grey
Tensile strength (ASTM D412)	
Longitudinal	: > 9N/mm ²
Transversal	: > 9N/mm ²
Elongation at break (ASTM D412)	
Longitudinal	: >650%
Transversal	: >650%

Puncture resistance

(ASTM E 154:93)

Maximum Load : > 700N

Water impermeability : No penetration

(BSEN 12390 P8) : @ 5 bar pressure

Tear resistance

(ASTM D624)

Longitudinal : >70N/mm

Transversal : >70N/mm

Lap joint strength : >400N/5cm

(welded) UEATc

Instructions for use

Surface preparation

Surfaces should be free from cavities and projecting nibs. All surfaces shall be dry and free from frost, surface laitence and contamination.

Application

The membrane layers are overlapped to achieve a minimum weld of 50mm. Hot air welding can be either hand applied or by means of automatic machines.

For additional details on installation and a list of Fosroc approved applicators refer to your local Fosroc office.

Estimating

Supply

Proofex ORG : 25m long x 2.10 m wide roll

Storage

All products have a shelf life of 12 months if stored in a cool, dry store, away from sources of heat, in the original unopened packing. It should be stored horizontally, not more than one pallet high.

Precautions

Health and Safety

There are no health hazards associated with the use of Proofex ORG.

For further information, please consult Material Safety Data Sheets for the above products.

Fire

Proofex ORG is non flammable



Fosroc Chemicals (India) Pvt. Ltd.

Head Office

"Sapthagiri Palace", No.38,
II & III Floor, 12th Cross,
CBI Road, Ganganagar North,
Bangalore 560 032

Important note :

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard terms and conditions of sale, copies of which may be obtained on request. Whilst Fosroc endeavours to ensure that any advice, recommendation specification or information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products whether or not in accordance with any advice, specification, recommendation or information given by it.

telephone

++91 80-23551500

fax

++91 80-23551510

e-mail

enquiryindia@fosroc.com

Regional Offices

Bangalore

"Sapthagiri Palace", No. 38
II & III Floor, 12th Cross,
CBI Road, Ganganagar North,
Bangalore 560 032.
Ph:080-23551500
Fax : 080-23551510

Mumbai

1401/1402, 14floor,
A-Wing'The Great Eastern Summit'
Sector-15, CBD, Belapur
Navi Mumbai 400 614
Ph: 022 -43406800-04

Delhi

D-166 Sector 10
Noida,
UP 201 301
Ph:0120-4270620
Fax: 033-2499-0280

Kolkata

304, Jodhpur Park
Kolkata 700 068
Ph:033-65343188