

constructive solutions

Flexible expansion joint membrane

Uses

Expoband One is a Hypalon membrane system which is designed to be bonded over movement joints or cracks in structures to prevent the passage of water. It is bonded in position using Nitomortar FCFs two-part epoxy adhesive. Exponand One is suitable for construction use and in repair/ remedial applications.

Advantages

- Accomodates continuous and pronounced cyclic movement
- Excellent resistance to weathering
- Can be applied to dry or damp surfaces

Standards Compliance

Water Regulations Advisory Service approved product.

Description

Expoband One is an un-reinforced Hypalon membrane incorporating a central release tape, available in 1mm thickness and widths of 100mm and 200mm. The 1mm thick membrane is supplied in a 25 metre roll.

When longer lengths are required Expoband One can be joined by hot welding. It is bonded to the structure on both sides of the joint using Nitomortar FCFS two-part epoxy adhesive.

Technical Data

Fosroc offers a comprehensive range of high performance, high quality technical products. In addition Fosroc offers a technical support package to specifiers and contractors which includes computer-aided design (CAD), standard details as well as on-site technical advice from staff with unrivalled experience in the industry.

Design Criteria

Example of a reservoir wall, sealed internally with Expoband One

Maintenance

There are no special requirements, however any damage should be repaired by exposing the damaged area, cleaning the surface and replacing the strip.

Properties

Form	: Elastomeric Strips	
Colour	: Light Grey	
Density	: 1.7 approximate	
Tensile Strength	: 7 N/mm²	
Elongation at break	: 400%	
Adhesion to concrete (with Nitromortar FCFS)	: >tensile strength of substrate	

Specification clauses

Where indicated on the drawings, joints shall be sealed with Expoband One flexible expansion joint membrane system supplied by Fosroc. Expoband One shall be installed strictly in accordance with the manufacturer's printed instructions

Application instructions

Joint preparation

Expansion joints must be packed with a firm, consolidated joint filler prior to laying the Expoband One. If necessary joints may be pre-sealed using a bituminous or elastomeric sealant. Ensure that any sealant used is capable of accommodating the anticipated joint movement. Where Expoband One has to be durned up parapets and the like, a splay should be provided so that the change in direction is smooth and progressive. (also known as Expoband H45)

Surface preparation

Concrete surfaces onto which the Expoband One is to be laid must be sound, frost and dust free. New concrete must be fully cured and free from curing compound. The concrete surface ideally should be wood float finished for the width of Expoband One and free from irregularities, with well deigned arises and no vertical misalignment between each side of the joint.

Prepare a suitable width of substrate slightly wider than the membrane width selected. Sharp arises should be ground down pencil round.

Remove all dirt, dust and laitance by rigorous wire brushing needle gun, abrasive blasting or grinding. Any spalling or honeycombing must be repaired prior to the application of the Expoband One system. Should the substate be wet, dry gently with a gas torch or hot air blower. Dampness should not reappear within 15 minutes for the substrate to be considered as being dry enough for the application of the Nitomortar FCFS. A maximum 25 mm width of masking tape applied adjacent to either arris will provide an increased unbonded width and greater movement potential if required.

Priming of concrete

Priming of concrete is not normally required with the Nitomortar FCFS/Expoband One system. The use of Fosroc Primer MS2 should be considered where there could be doubt about porosity or condition of the concrete. Apply Fosroc Primer MS2 by brush, working well in, to a width of 25mm either side of the membrane. Fosroc Primer MS2 should be left for about 40 to 60 minutes (depending upon temperature) to allow evaporation of the primer solvent prior to the application of the Nitomortar FCFS adhesive.

If the primer has been left longer than 8 hours or has become contaminated with dust, the surface must be reprimed. The rate of cure of Fosroc Primer MS2 is temperature dependent. Ideally the substrate should be above 10°C to ensure a reasonable cure rate, however, this primer can be applied when substrate temperatures are 5°C and rising.

Preparation of the membrane

This operation is vital to the adhesion and performance of the Expoband One system. Measure and cut the length of Expoband One to suit the joint. The Expoband One hypalon membrane must be prepared by thoroughly wiping both faces with Fosroc Solvent 102 and a clean cloth. DO NOT use excessive quantities of solvent. Allow 1 hour to dry before placing.

Mixing and application of the adhesive

Transfer the entire contents of Part B of Nitomortar FCFS adhesive into the Part A container and mix thoroughly using a slow speed drill and Fosroc paddle stirrer for 4 minutes, stopping to scrape down the sides of the container. When mixed, the adhesive should be a uniform grey colour.

Use masking tape at extremities and along centre line of joint. Apply mixed Nitomortar FCFS using a serrated spreader. Remove central masking tape immediately and position Expoband One membrane into the Nitomortar FCFS adhesive.

Roll firmly to displace trapped air and to ensure extrusion of Nitomortar FCFS through the edge perforations.

Apply a second layer of Nitomortar FCFS to the full width of the top surface of membrane. Remove central release firlm from membrane. Finally remove outer edge masking tapes and feather edge the Nitomortar FCFs.

Jointing the Expoband One membrane

The surfaces to be jointed must be clean and wiped with Fosroc Solvent 102 prior to jointing. For heat welded joints, a 50 mm overlap should be used. Welding is carried out using a proprietary hot air welding tool. The tool should be sent to the correct heat output by trial to achieve a satisfactory weld.

The faces of the overlap are heated by moving the welding tool along the joint and, simultaneously, pressure should be applied by roller to the heated overlap to ensure that the faces are fused together. After application the Expoband One system should be allowed to cure for 28 days at 7°C before permanent contact with potable water.



Expoband One*

(also known as Expoband H45)

Ancillary materials and equipment

- Nitomortar FCS
- Fosroc Solvent 102
- Fosroc Primer MS2
- Slow speed drill and Fosroc paddle stirrer
- Adhesive spreader with 2 to 3 mm serrations
- Hot air welding gun and roller

Limitations

Joint layouts incorporating Expoband One should be kept as simple as possible to allow for site joints to be restricted to straight butt joints. Avoid complex changes of angle or skew giving rise to difficulty in jointing and installation.

Estimating

Supply		
. 25	m x 100mm x 1mm 5m x 200mm x 1mm 5m x 100mm x 2mm	
15m x 200mm x 2mm		
Coverage Nitomortar FCFS (based on a 2mm spread of adhesive above and below the membrane)		
For 100mm wide :	5 to 6 linear metres per 2 litres Nitomortar FCFS	
For 200mm wide :	2.5 to 3.5 linear metres per 2 litres Nitomortar FCFS dependent upon surface roughness and film thickness	
Fosroc Primer MS2 :	10m²/litre	

The coverage figures are theoretical - due to wastage factors and the variety variety and nature of substrates, practical coverage figures may be substantially reduced.

Storage

Expoband One should be stored in original unopened packaging in cool dry conditions, away from sunlight. Fosroc

Primer MS2 should be stored in accordance with the Highly Flammable Liquids and Liquified Petroleum Gases Regulations 1972.

Precautions

Health and Safety

Expoband One

There are no known hazards associated with this product in normal use.

Fire

Fosroc Primer MS2 and Fosroc Solvent 102 are flammable. Do not expose to naked flames or other sources of ignition. No Smoking. Containers should be tightly sealed when not in use. In the event of fire, extinguish with CO_2 or foam.

Additional Information

Fosroc manufactures a wide range of complementary products which include :

- Waterproofing membranes & waterstops
- Joint sealants & filler boards
- cementitious & epoxy grouts
- specialised flooring materials.

Fosroc additionally offers a comprehensive package of products specially designed for the repair and refurbishment of damaged concrete. Fosroc's 'Systematic Approach' to concrete repair features the following :

- hand-placed repair mortars
- spray grade repair mortars
- fluid micro-concretes
- chemically resistant epoxy mortars
- anti-carbonation/anti-chloride protective coatings
- chemical and abrasion resistant coatings.

* Dinotes trademark of Fosroc International Ltd.



Expoband One*

(also known as Expoband H45)



Head Office

Important note :

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard terms and conditions of sale, copies of which may be obtained on request. Whilst Fosroc endeavours to ensure that any advice, recommendation specification or information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products whether or not in accordance with any advice, specification, recommendation or information given by it.

telephone	fax	e-mail
++91 80-23551500	++91 80-23551510	enquiryindia@fosroc.com

Regional Offices

Bangalore

Bangalore 560 032

"Sapthagiri Palace", No. 38 II & III Floor, 12th Cross, CBI Road, Ganganagar North, Bangalore 560 032. Ph:080-23551500 Fax : 080-23551510

Fosroc Chemicals

(India) Pvt. Ltd.

"Sapthagiri Palace", No.38, II & III Floor, 12th Cross, CBI Road, Ganganagar North,

> *Mumbai* 1401/1402, 14 Floor, A-Wing'The Great Eastern Summit' Sector-15, CBD, Belapur Navi Mumbai 400 614 Ph: 022 -43406800-04

Noida D-166 Sector 10 Noida, UP 201 301 Ph:0120-4270620

Kolkata

304, Jodhpur Park Kolkata 700 068 Ph:033-65343188 Fax: 033-2499-0280

