# **Nitobond PC**



constructive solutions

# Thixotropic epoxy adhesive

#### Uses

Bonding segmented concrete bridges / structures to speed up construction and provide a structural and water resistant joint. Can be used for pointing Stone masonry joints to retain structural integrity .

### **Advantages**

- Excellent squeezability
- High bond strength
- Fast cure
- Tolerant to damp surfaces
- Wide range of temperature applications

# Standards compliance

Nitobond PC fully conforms to meets the FIP specifications.

### **Description**

Nitobond PC thixotropic epoxy adesive is a 2 pack solvent free epoxy resin system consisting of a white base and black hardener in preweighed quantities for easy onsite mixing. The product is available in three grades :

- Nitobond PC20 Fast set for application between 5°C to 20° C
- Nitobond PC 30 Medium Fast set for application between 15°C to 30°C
- Nitobond PC40 Slow set for application between 25°C to 40°C

# **Technical Support**

Fosroc provides a technical advisory service supported by a team of specialists in the field.

### **Properties**

Colour		Base Hardener Mixed	<ul><li>W hite</li><li>Black</li><li>Grey</li></ul>	
Mixed Density		1.75-1.8	3	
Heat Resistance @ 50°C		18MPA		
Cure characteristics				
R	ecommended	Pot life **	Open	
	Application	(Mins.)	Time	
	Temperature		(Mins.)	
Nitobond PC20	5°C-20°C	30 at 20°C	60 at 20°C	
Nitobond PC30	15°C-30°C	30 at 30°C	60 at 30°C	
Nitobond PC40	25°C-40°C	35 at 40°C	70 at 40°C	
Daniel guage flow		1mm		

# \*\* for 100 g of mixed material

# **Mechanical properties**

Squeezability@25°C, 15 Kgload 4175mm²					
Compressive	@	24 hours	68N/mm²		
Strength (FIP 5.6)	@	7days	85N/mm <sup>2</sup>		
Tensile bending strength (FIP 5.14)		Concrete failure			
Shear Strength (FIP 5.15)	21N/mm²				

# **Application instructions**

### **Surface Preparation**

Concrete should be mechanically sound and free from contamination, such as free water, mould, oil or grease, laitence and dust. Grit blasting is recommended. Sections to be bonded should be checked for good alignment. A 'dry r un' before the first application of the adhesive is recommended to ensure correct timing.

# **Mixing**

The base and hardener into a suitable container shall be emptied and mixed with a paddle and slow speed heavy duty drill, ensuring the sides are scraped down. A uniform grey colour should be obtained after mixing thoroughly.

# **Application**

The mixed adhesive is applied to both surfaces to be bonded with a serrated trowel or other suitable spreader.

The joint should be closed immediately, if this is not achieved the surface of the adhesive should be slightly so rate hed immediately prior to closing the joint to expose fresh adhesive. The joint must be closed within the open time of the adhesive. On site monitoring of the operation using lapped asbestos cement panels is recommended.

## **Cleaning of Application Equipment**

Tools and equipment should be cleaned immediately after use with Nitoflor Sol.

# **Estimating**

# **Packaging**

30 Ltr. bulk packs and 3.7 L standard packs.

## Coverage

Approximately 2 L/m<sup>2</sup> at 2 mm thickness

# **Nitobond PC**

### **Storage**

### **Shelf Life**

12 months if stored below 35°C in unopened containers.

### **Precautions**

# **Health and Safety**

Some people are sensitive to epoxy resin system and may develop dermatitis. Direct contact with eyes will cause irritation and may cause serious damage if left untreated. Any eye contamination should be washed thoroughly with water and immediate medical attention should be sought. Gloves, barrier creams and eye protection should always be used when handling Nitobond PC and Nitoflor Sol.

If contact with skin occurs, a resin removing cream should be used, followed by washing with soap and water. Solvent shall not be used.

#### Fire

Nitobond PC base and hardener are nonflammable. Nitoflor Sol is flammable. Do not use near naked flames. No smoking.

### Flash Points:

Nitobond PC	Base	100°C
(Abel open cup )		
Nitobond PC	Hardener	100°C
(Abel open cup )		
Nitoflor Sol	Solvent	33°C
(Abel closed cup		
method IP 33)		

### **Additional information**

Nitobond PC is a part of wide range of adhesives, repair materials, sealing and waterproofing compounds, grouts and flooring products manufactured by Fosroc for the construction industry.

Separate datasheet is available on these products.



# Fosroc Chemicals (India) Pvt. Ltd.

Head Office

"Sapthagiri Palace", No.38, II & III Floor, 12th Cross, CBI Road, Ganganagar North, Bangalore 560 032

# Important note:

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard terms and conditions of sale, copies of which may be obtained on request. Whilst Fosroc endeavours to ensure that any advice, recommendation specification or information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products whether or not in accordance with any advice, specification, recommendation or information given by it.

telephone	fax	e-mail
++91 80-42521900	++91 80-23551510	enquiryindia@fosroc.com

# Regional Offices

# **Bangalore**

"Sapthagiri Palace", No. 38 II & III Floor, 12th Cross, CBI Road, Ganganagar North, Bangalore 560 032. Ph:080-42521900

Fax: 080-23551510

### Mumbai

1401/1402, 14th Floor, A-Wing'The Great Eastern Summit' Sector-15, CBD, Belapur Navi Mumbai 400 614 Ph: 022 -43406800-04

### Noida

D-166 Sector 10 Noida, UP 201 301 Ph:0120-4270620

### Kolkata

304, Jodhpur Park Kolkata 700 068 Ph:033-65343188 Fax: 033-2499-0280





INDIA/2012/0908/E